

## APPLICATION PROCESS

### FINE WALL SYSTEM (Walls – Vertical surfaces)

#### Substrate preparation

Follow the steps of the MEDIUM application system. Then sand thoroughly and clean with a vacuum cleaner.

#### Mix Preparation

Empty the entire pigment into a 10kg bucket and mix with a low-speed stirrer (mixer) for 2 minutes. Then fill the pigment bottle with **an additional 200ml** of water to make use of all remaining pigment in the container, and add it to the paste, stirring well for another **2 minutes**.

Ensure thorough homogenization of the material with the pigment throughout the bucket and that the material has a thick consistency before starting application.

#### Application Method

##### 1 COAT

Before applying the Granitech **FINE**, it is recommended to apply a coat of **MONOPRO TERRAZZO VARNISH** for better adhesion.

Apply a thin coat evenly to seal the pores. There should be no excess material left on the application surface.

After completing the application, if any dark spots appear at certain points, allow the material to dry and sand with 120-150 grit sandpaper. Then, wearing disposable gloves, apply a very small amount of material locally and spread it with your hands.

Allow it to dry, check if sanding is needed, and once satisfied with the result, proceed with the application of the varnish.

#### Varnish

##### X MATTE WATER

Mix the contents of **A** with the contents of **B** using a low-speed mixer until they are well homogenized.

Apply the varnish in one coat for indoor walls, in at least two coats for outdoor areas and areas with increased humidity (e.g., bathroom), with a minimum of 24 hours between each coat.

Finally, we deliver the space for use after 4 days from the final coat.

**CAUTION!** The varnish reaches its final strength within 14 to 30 days.

#### Consumption

~3 Kg / m<sup>2</sup>

#### Cleaning

Tools, containers, etc., should be cleaned with water while **TERRAZZO Granitech** is still wet. After hardening, cleaning should be done only using mechanical means.

#### Recommendations

The application of **TERRAZZO Granitech** should be carried out in mild weather conditions. Do not apply in case of imminent rain, high wind levels, or direct sunlight. Avoid applying at temperatures below 12°C or above 32°C, as well as in relative humidity above 70%.

#### FINE PRINT

Throughout the duration of work in the area, protect the surfaces where TERRAZZO Granitech has been applied with nylon and cardboard. The corrugated side **always faces upwards**.

The material reaches its final strength within 30 days.

**CAUTION** with point loads. Protect the floor by placing pads under each piece of furniture or heavy object for proper maintenance of the material and to avoid marks.

Clean the surfaces with any cleaner. If using chlorine, it is recommended to clean the surface again with clean water to remove any residual chlorine. Otherwise, use cleaners with a neutral pH.